

on F/c Cow Leather - 2.0% Shade



POPLON (India)

POPLON / POPNIL DYES

POPLON (India)

on F/c Cow Leather - 2.0% Shade



Yellow 2RL



Orange G




Red PR



Bordeaux FBBR



Dark Green B



Dark Green FBN



Havana G



Orange RL



Pink B



Scarlet LN



Olive Brown GBR



Blue 2 G

POPLON / POPNIL DYES

POPLON (India)

on F/c Cow Leather - 2.0% Shade



Dark Blue FBN



Beige Brown R



Brown 3 GN



Brown FBRL



Dark Brown FBTI



Dark Brown FBCN



Beige LT



Olive Brown FBN



Yellow Brown 2RI



Dark Brown FBR



Brown FBFR



Dark Brown BL. Conc.

POPLON / POPNIL DYES

POPLON (India)

on F/c Cow Leather - 2.0% Shade



Brown NGB



Yellow 3RLN



Red FBG



Black SRL



Black NT SPL



Yellow GTP



Yellow GR



Black PBO



Grey BEI



Grey PBL

POPLON / POPNIL DYES

POPLON (India)

on F/c Cow Leather - 2.0% Shade

	ITEM, NAME	COLOUR FASTNESS PROPERTIES OF POPLON DYES				
	POP LEATHER DYES	LIGHT	WASHING	PERSPIRATION	PENETRATION	PVC MIGRATION
1	Yellow RS	4	4	4	2-3	-
2	Yellow 5GNE	4	4	3-4	3	4
3	Yellow 2RLNJ	4	4	3-4	3-4	-
4	Yellow 2R	2-3	2-3	2-3	2-3	-
5	Yellow P	4	4	4	3	-
6	Bright Yellow JS	3	2-3	2-3	4	-
7	Orange 7GLL	4-5	3-4	2-3	3	-
8	Orange PS	4	3	2	5	2-3
9	Orange II	4	3	2	5	3-4
10	Orange 5R	4	4	4	3	4
11	Scarlet N	2-3	4	3	2	2-3
12	Red GF	3	4	3	2	2-3
13	Blood Red 4B	4	4	3	3	3-4
14	Blood Red PF	4	4	3	3	4
15	Red 5B	4	4	3-4	3	3-4
16	Red BNF	3	4	3	2	3
17	Red 3BN	4	3-4	3	2	3
18	Cherry Red B	4-5	4	4	3	4
19	Bright Pink P	4-5	4-5	4	3	4
20	Red Brown RN	3-4	3-4	3-4	2	2-3
21	Bordeaux V conc	4	3	4	2-3	3-4
22	Red Violet	4-5	4	3	2	4-5
23	Maroon V	5	4-5	4	3	3-4
24	Brilliant Green 3GM	2-3	3	3	3	-
25	Green P	3	3	3	5	2-3
26	Bottle Green BG	3-4	4	3	4	-
27	Patent Blue AS	2-3	2-3	2-3	3	-
28	Olive Brown SG	4-5	4	4	3	4
29	Dark Green BG	3-4	3	3	4	3-4

on F/c Cow Leather - 2.0% Shade

	ITEM, NAME	COLOUR FASTNESS PROPERTIES OF POPLON DYES				
	POP LEATHER DYES	LIGHT	WASHING	PERSPIRATION	PENETRATION	PVC MIGRATION
30	Violet 68D	2-3	2-3	3	2	2-3
31	Brilliant Blue FFS	2-3	2-3	3	2	-
32	Navy Blue	5	3	3	3	4-5
33	Marine Blue N	4-5	4	4	3	4-5
34	Blue NJ	3-4	3	3	3	-
35	Royal Blue JM	4-5	4	3	3	3-4
36	Brown SBL	3-4	3	2-3	3	-
37	Beige Brown SS	3-4	2-3	2-3	2	-
38	Brown BS	3	3	3	3	-
39	Tan Brown S	2-3	2-3	3	3	-
40	Brown IMB	4	4	4	3	3-4
41	Brown NJ	4-5	4-5	4	4	3-4
42	Brown GN	4-5	4	4-5	4	4
43	Brown EB (G)	3-4	4	3-4	3	3-4
44	Brown EBL	4-5	4-5	4	5	4-5
45	Brown G	5	4-5	4-5	4-5	4-5
46	Brown GRE	4-5	4-5	4	3	3
47	Brown HEDG	4	3-4	3-4	3	3-4
48	Brown FHW	5	3-4	3-4	3	3-4
49	Brown PBT	3-4	4	3-4	4	2
50	Brown FBT	4-5	3-4	4	3	4
51	Dark Brown GRP	4	3-4	3-4	3	-
52	Dark Brown 75N	4	3	3-4	3-4	3-4
53	Dark Brown 3K	4	3	3	3-4	2-3
54	Dark Brown FB	4-5	4	3-4	3	4
55	Dark Brown BGS CONC	3-4	3	3	2-3	-
56	Dark Brown ABR	4-5	4	4	4-5	4-5
57	Dark Brown B	4-5	4	4	3-4	2-3
58	Dark Brown AKD	4-5	4	4	3-4	-

on F/c Cow Leather - 2.0% Shade

	ITEM, NAME	COLOUR FASTNESS PROPERTIES OF POPLON DYES				
	POPLON & POPNIL DYES	LIGHT	WASHING	PERSPIRATION	PENETRATION	PVC MIGRATION
1	Yellow 2RL	4	4	3-4	2-3	4-5
2	Havana G	4	4	3-4	3	5
3	Orange G	5	4	4	3-4	4-5
4	Orange RL	4-5	3-4	4	2-3	4-5
5	Red PR	4-5	4	4	2	4-5
6	Pink B	4-5	3-4	3-4	3	4
7	Bordeaux FBBR	5	4	4	2-3	4-5
8	Scarlet LN	4-5	3-4	3-4	3	4
9	Dark Green BG	4	4	4	3	4
10	Olive Brown GBR	4-5	4	4	3	-
11	Dark Green FBN	4	4	4	3	4
12	Blue 2G	4	4	4	3	4
13	Dark Blue FBN	4	3-4	3-4	3	4-5
14	Beign LT	4-5	4	4	2-3	4
15	Beige Brown R	4	4	4	3	4-5
16	Olive Brown FBN	4	4	4	3	4-5
17	Brown 3GN	4	4	4	2-3	4-5
18	Yellow Brown 2RI	4-5	3-4	4	3	4-5
19	Brown FBRL	4-5	4	4	4	4
20	Dark Brown FBR	4-5	4	4	3-4	4-5
21	Dark Brown FBTI	5	3-4	3-4	3	4-5
22	Brown FBFR	5	4	4	3	4-5
23	Dark Brown FBCN	4-5	4	3-4	4	-
24	Dark Brown BL Conc	5	4-5	4	2-3	4
25	Brown NGB	3-4	4	4	2-3	4-5
26	Yellow GTP	5	4	3-4	3	4-5
27	Yellow 3 RLN	4	3-4	4	3	4-5
28	Yellow GR	4-5	4	5	4-5	4
29	Red FBG	4-5	4	4	2-3	4